



VAG A T E X [®]
I T A L I A

TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

ARTICLE:	VGT 330 TP - FIRST
COMPOSITION:	67% VI 33% LI
WEIGHT G/M LIN.:	955 gr/mtl
REPEAT(WARP/WEFT):	no
METERS PER ROLL:	25/30 mt
WIDHT CM:	140

REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 3/4 Color degradation after 6000 giri: 3/4 END POINT (rubs): > 25.000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 3/4 At 2000 rubs: 3/4
Colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5
Colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5 dry: 4 wet: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): Shortening (warp):
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6 warp mm < 6
Fire Resistance	back coating: - IMO FTP code 307(88):2010 Part. 8 Annex 1 MATCH & CIGARETTE - CALIFORNIA TEST TB 117:2013
Environmental benefits	- No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Compiles with REACH regulation.
Sustainability	ECO-PATH (available on request)
Available teflon treatment	(on request with surcharge)
Type of finish used	airo water + equalized steam
Tariff code	5516920000
Raw Material & Weaving	Made in Italy

--	--	--	--	--

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 2004614-001
REPORT DATE 22/12/2020
ACCEPTANCE DATE 18/12/2020
START TEST DATE 18/12/2020
END TEST DATE 22/12/2020
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION FABRIC ART. VGT/330 FIRST TP FR

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD	ACCREDIA
6011001 Ignitability of upholstery fabric - California test	TB 117:2013	

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(*) = Test marked with asterisk are not accredited ACCREDIA. Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The sample description content is under the full responsibility of the customer and not of the laboratory.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR.	2004614-001
REPORT DATE	22/12/2020
ACCEPTANCE DATE	18/12/2020
START TEST DATE	18/12/2020
END TEST DATE	22/12/2020
SAMPLING BY CUSTOMER	

NOTES ANALYTICAL TESTS

- **6011001 Ignitability of upholstery fabric - California test** **TB 117:2013**
Acclimatization: At least 24 hours at 21±3 °C and <55 R.H. %.
Codes used:
SE: Self-extinguished;
SB45: Smolder beyond 45 min;
TOF: Transitions to open flaming;
MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames.
The data are referred to TB 117:2013 - Section NR.1
Filling material: PU-nonFR (28-29,6 Kg/m³) supplied by the laboratory.

GENERAL NOTES

(*) = Test marked with asterisk are not accredited ACCREDIA. Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The sample description content is under the full responsibility of the customer and not of the laboratory.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 2004614-001
REPORT DATE 22/12/2020
ACCEPTANCE DATE 18/12/2020
START TEST DATE 18/12/2020
END TEST DATE 22/12/2020
SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
6011001 Ignitability of upholstery fabric - California test			TB 117:2013
Initial - Specimen 1 - Char length	inch	0,1	
Initial - Specimen 2 - Char length	inch	0	
Initial - Specimen 3 - Char length	inch	0,1	
Initial - Specimen 1 - SE	Yes/No	YES	
Initial - Specimen 2 - SE	Yes/No	YES	
Initial - Specimen 3 - SE	Yes/No	YES	
Initial - Specimen 1 - SB45	Yes/No	NO	
Initial - Specimen 2 - SB45	Yes/No	NO	
Initial - Specimen 3 - SB45	Yes/No	NO	
Initial - Specimen 1 - TOF	Yes/No	NO	
Initial - Specimen 2 - TOF	Yes/No	NO	
Initial - Specimen 3 - TOF	Yes/No	NO	
Final class		PASS	

----- **END OF REPORT** -----

(*) = Test marked with asterisk are not accredited ACCREDIA. Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The sample description content is under the full responsibility of the customer and not of the laboratory.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1903435-001
REPORT DATE 30/09/2019
ACCEPTANCE DATE 26/09/2019
START TEST DATE 26/09/2019
END TEST DATE 30/09/2019
SAMPLING BY CUSTOMER

TEST REPORT

SAMPLE DESCRIPTION FABRIC ART. VGT/330 FIST BIANCO

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD
6012041 Assessment of the ignitability of upholstery fabric - Cigarette	IMO FTP code 307(88):2010 Part. 8 Annex 1
6012042 Assessment of the ignitability of upholstery fabric - Match	IMO FTP code 307(88):2010 Part. 8 Annex 1

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



The results contained in this report relates **only to the sample tested** and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR.	1903435-001
REPORT DATE	30/09/2019
ACCEPTANCE DATE	26/09/2019
START TEST DATE	26/09/2019
END TEST DATE	30/09/2019
SAMPLING BY CUSTOMER	

NOTES ANALYTICAL TESTS

- **6012041 Assessment of the ignitability of upholstery fabric - Cigarette** **IMO FTP code 307(88):2010 Part. 8 Annex 1**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; Acclimatization: At least 16 hours at 20 ± 5 °C e $50 \% \pm 20 \%$ RH; Ignition source (i.s.): Ignition source - smouldering cigarette.
Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.
The test was conducted without the pretreatment at the request of the customer, in derogation from the standard.
The test is therefore indicative.
Off ignition source.
- **6012042 Assessment of the ignitability of upholstery fabric - Match** **IMO FTP code 307(88):2010 Part. 8 Annex 1**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; Acclimatization: At least 16 hours at 20 ± 5 °C e $50 \% \pm 20 \%$ RH; Ignition source (i.s.): Ignition source - Match equivalent flame.
Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.
The test was conducted without the pretreatment at the request of the customer, in derogation from the standard.
The test is therefore indicative.

GENERAL NOTES

The results contained in this report relates **only to the sample tested** and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1903435-001
REPORT DATE 30/09/2019
 ACCEPTANCE DATE 26/09/2019
 START TEST DATE 26/09/2019
 END TEST DATE 30/09/2019
 SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
6012041 Assessment of the ignitability of upholstery fabric - Cigarette			IMO FTP code 307(88):2010 Part. 8 Annex 1
Pretreatment		The test was conducted without the pretreatment at the request of the customer, in derogation from the standard.	
Kind of sample		Cover fabric	
Test 1 - Combustion with flame	Yes/No	NO	
Test 1 - Progressive smouldering	Yes/No	NO	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	Yes/No	NO	
Test 2 - Progressive smouldering	Yes/No	NO	
Test 2 - Result		PASS	
6012042 Assessment of the ignitability of upholstery fabric - Match			IMO FTP code 307(88):2010 Part. 8 Annex 1
Pretreatment		The test was conducted without the pretreatment at the request of the customer, in derogation from the standard.	
Kind of sample		Cover fabric	
Test 1 - Combustion with flame	s	0	
Test 1 - Progressive smouldering	s	11	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	s	0	
Test 2 - Progressive smouldering	s	8	
Test 2 - Result		PASS	

----- **END OF REPORT** -----

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it