



VAG A T E X [®]
I T A L I A

TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

ARTICLE:	VGT 335 TP - CUERO 1,4 mm
COMPOSITION:	60% PA 40% PU
WEIGHT G/M LIN.:	825 gr/mtl
REPEAT(WARP/WEFT):	NO
METERS PER ROLL:	30mt (33 yards)
WIDHT CM:	140

REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 4 Color degradation after 6000 giri: 4 END POINT (rubs): > 100.000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 4/5 At 2000 rubs: 5
Colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5
Colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5 dry: 4 wet: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): +/-3% Shortening (warp): +/-3%
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6 warp mm < 6
Fire Resistance	- A: BRITISH 5852 CIGRETTE & MATCH - B: EN1021 CIGARETTE & MATCH - C: TB 117 CALIFORNIA - D: IMO FTP Part. 8 Annex 1 CIGARETTE & MATCH
Environmental benefits	- No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Complies with REACH regulation.
Sustainability	TEST OEKO TEX AVAIBLE
Available teflon treatment	YES - OIL AND WATER REPELLENT
Type of finish used	
Tariff code	5903909990
Raw Material & Weaving	Made in Italy



MESSRS.:
VAGATEX ITALIA SRL
VIA SCARPETTINI 204
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1500352-001
REPORT DATE 16/02/2015
ACCEPTANCE DATE 10/02/2015
START TEST DATE 10/02/2015
END TEST DATE 16/02/2015
SAMPLING BY CUSTOMER

TEST REPORT

SAMPLE DESCRIPTION: 335 CUERO

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY ¹
6011002 Assessment of the ignitability of upholstery fabric - California test			
Method: TB 117:2013 - Assessment of the ignitability of upholstery fabric - California test			
Initial - Specimen 1 - Char length	inch	0,3	
Initial - Specimen 2 - Char length	inch	0,4	
Initial - Specimen 3 - Char length	inch	0,4	
Initial - Specimen 1 - SE	Yes/No	YES	
Initial - Specimen 2 - SE	Yes/No	YES	
Initial - Specimen 3 - SE	Yes/No	YES	
Initial - Specimen 1 - SB45	Yes/No	NO	
Initial - Specimen 2 - SB45	Yes/No	NO	
Initial - Specimen 3 - SB45	Yes/No	NO	
Initial - Specimen 1 - TOF	Yes/No	NO	
Initial - Specimen 2 - TOF	Yes/No	NO	
Initial - Specimen 3 - TOF	Yes/No	NO	
Replacement - Specimen 1 - Char length	inch	0,4	
Replacement - Specimen 2 - Char length	inch	0,4	
Replacement - Specimen 3 - Char length	inch	0,5	
Replacement - Specimen 1 - SE	Yes/No	YES	

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

		REPORT NR.	1500352-001
		REPORT DATE	16/02/2015
TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
Replacement - Specimen 2 - SE	Yes/No	YES	
Replacement - Specimen 1 - SE	Yes/No	YES	
Replacement - Specimen 1 - SB45	Yes/No	NO	
Replacement - Specimen 2 - SB45	Yes/No	NO	
Replacement - Specimen 2 - SB45	Yes/No	NO	
Replacement - Specimen 1 - TOF	Yes/No	NO	
Replacement - Specimen 2 - TOF	Yes/No	NO	
Replacement - Specimen 3 - TOF	Yes/No	NO	
Final class		PASS	

Codes used:

SE: Self-extinguished;

SB45: Smolder beyond 45 min;

TOF: Transitions to open flaming;

MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames. The data are referred to TB 117:2013 - Section NR.1

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR.

1500352-001

REPORT DATE

16/02/2015

6012001 Assessment of the ignitability of upholstery fabric - Cigarette

Method: BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Cigarette

Kind of sample		COVER FABRIC
Test 1 - Combustion with flame	sec	0"
Test 1 - Progressive smouldering	sec	0"
Test 1 - Result		PASS
Test 2 - Combustion with flame	sec	0"
Test 2 - Progressive smouldering	sec	0"
Test 2 - Result		PASS

Off ignition source.

*Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.
Pretreatment: None*

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989, 1993 and 2010, Schedule 4 - Part 1 (i.s. 0); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR.

1500352-001

REPORT DATE

16/02/2015

6012002 Assessment of the ignitability of upholstery fabric - Match

Method: BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Match

Kind of sample		COVER FABRIC
Test 1 - Combustion with flame	sec	0"
Test 1 - Progressive smouldering	sec	3"
Test 1 - Result		PASS
Test 2 - Combustion with flame	sec	0"
Test 2 - Progressive smouldering	sec	3"
Test 2 - Result		PASS

Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR.

1500352-001

REPORT DATE

16/02/2015

6012021 Assessment of the ignitability of upholstery fabric - Cigarette

Method: EN 1021-1:2006 - Assessment of the ignitability of upholstery fabric - Cigarette

Test 1 - Combustion with flame	sec	0"	
Test 1 - Progressive smouldering	sec	0"	
Test 1 - Result		N.I.	
Test 2 - Combustion with flame	sec	0"	
Test 2 - Progressive smouldering	sec	0"	
Test 2 - Result		N.I.	

Off ignition source.

*Filling material: PU FR HR30S (30-33 Kg/m³) supplied by the laboratory.
Pretreatment: None*

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR. 1500352-001
REPORT DATE 16/02/2015

6012031 Assessment of the ignitability of upholstery fabric - Match

Method: EN 1021-2:2006 - Assessment of the ignitability of upholstery fabric - Match

Test 1 - Combustion with flame	sec	0"
Test 1 - Progressive smouldering	sec	6"
Test 1 - Result		N.I.
Test 2 - Combustion with flame	sec	0"
Test 2 - Progressive smouldering	sec	5"
Test 2 - Result		N.I.

Filling material: PU FR HR30S (30-33 Kg/m³) supplied by the laboratory.
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989, 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

Unrepeatable tests to exhaustion test material.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

END OF REPORT

Managing Director

Patrizia Rosati

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1800783-001
REPORT DATE 07/03/2018
ACCEPTANCE DATE 01/03/2018
START TEST DATE 01/03/2018
END TEST DATE 07/03/2018
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION VGT 804 TP/FR CUERO FLAME RETARDANT

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD
6012041 Assessment of the ignitability of upholstery fabric - Cigarette	IMO FTP code 307(88):2010 Part. 8 Annex 1
6012042 Assessment of the ignitability of upholstery fabric - Match	IMO FTP code 307(88):2010 Part. 8 Annex 1

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR.	1800783-001
REPORT DATE	07/03/2018
ACCEPTANCE DATE	01/03/2018
START TEST DATE	01/03/2018
END TEST DATE	07/03/2018
SAMPLING BY CUSTOMER	

NOTES ANALYTICAL TESTS

- **6012041 Assessment of the ignitability of upholstery fabric - Cigarette** **IMO FTP code 307(88):2010 Part. 8 Annex 1**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; Acclimatization: At least 16 hours at 20 ± 5 °C e $50 \% \pm 20 \%$ RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.
Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.
Off ignition source.
- **6012042 Assessment of the ignitability of upholstery fabric - Match** **IMO FTP code 307(88):2010 Part. 8 Annex 1**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e $50 \% \pm 20 \%$ RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.
Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.

GENERAL NOTES

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1800783-001
REPORT DATE 07/03/2018
 ACCEPTANCE DATE 01/03/2018
 START TEST DATE 01/03/2018
 END TEST DATE 07/03/2018
 SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
6012041 Assessment of the ignitability of upholstery fabric - Cigarette			IMO FTP code 307(88):2010 Part. 8 Annex 1
Pretreatment		Water soak 40 °C - 30 min	
Kind of sample		COVER FABRIC	
Test 1 - Combustion with flame	Yes/No	NO	
Test 1 - Progressive smouldering	Yes/No	NO	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	Yes/No	NO	
Test 2 - Progressive smouldering	Yes/No	NO	
Test 2 - Result		PASS	
6012042 Assessment of the ignitability of upholstery fabric - Match			IMO FTP code 307(88):2010 Part. 8 Annex 1
Pretreatment		Water soak 40 °C - 30 min	
Kind of sample		COVER FABRIC	
Test 1 - Combustion with flame	s	0	
Test 1 - Progressive smouldering	s	7	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	s	0	
Test 2 - Progressive smouldering	s	8	
Test 2 - Result		PASS	

----- **END OF REPORT** -----

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

MESSRS.:
VAGATEX ITALIA SRL
VIA SCARPETTINI 204
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1600300-001
REPORT DATE 09/02/2016
ACCEPTANCE DATE 28/01/2016
START TEST DATE 28/01/2016
END TEST DATE 09/02/2016
SAMPLING BY CUSTOMER

TEST REPORT

SAMPLE DESCRIPTION: VGT 335 TPC - CUERO

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY ¹
4016003 Detection of the banned azo colourants on coloured textile commodities			
Method: UNI EN ISO 14362-1:2012 + UNI EN ISO 14362-3:2012 (*)			
4 - Aminodiphenyl	mg/Kg	N.D.	
Benzidine	mg/Kg	N.D.	
4 - Chloro-o-toluidine	mg/Kg	N.D.	
2 - Naphthylamine	mg/Kg	N.D.	
or - Aminoazotoluene	mg/Kg	N.D.	
2 - Amino - 4 - Nitrotoluene	mg/Kg	N.D.	
p - Chloroaniline	mg/Kg	N.D.	
2.4 - Diaminoanisole	mg/Kg	N.D.	
4.4 - Diaminodiphenylmethane	mg/Kg	N.D.	
3.3 - Dichlorobenzidine	mg/Kg	N.D.	
3.3 - Dimettossibenzidina	mg/Kg	N.D.	
3.3 - Dimethylbenzidine	mg/Kg	N.D.	
4,4 - metilene - di - o - toluidina	mg/Kg	N.D.	
p - Cresidina	mg/Kg	N.D.	
4,4 - Methylene-bis - (2 - Chloroaniline)	mg/Kg	N.D.	
4.4 - Oxydianiline	mg/Kg	N.D.	
4.4 - Thiodianiline	mg/Kg	N.D.	

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

		REPORT NR.	1600300-001
		REPORT DATE	09/02/2016
TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
o - Toluidine	mg/Kg	N.D.	
2.4 - Toluilendiammina	mg/Kg	N.D.	
2,4,5 - Trimetilnilina	mg/Kg	N.D.	
2.4 - Xylidina	mg/Kg	N.D.	
2.6 - Xylidina	mg/Kg	N.D.	
0 - Anisidine	mg/Kg	N.D.	
4 - Aminoazobenzene	mg/Kg	N.D.	
Final result	mg/Kg	N.D.- PASS	

N.d. - Not detectable; Final Result negative <30 ppm for amine, positive end result> 30 ppm for amine, in the test sample are not present azo dyes that the conditions of analysis may release one or more banned amines in concentrations greater than or equal to 30 ppm; The Xylidine are provided exclusively by private labels; Instrument: HPLC with diode detector (DAD) (HPLC-DAD); TLC plates (Silica Gel Stationary Phase).

4005041 Formaldehyde content

Method: UNI EN ISO 14184-1:2011

Formaldehyde content	mg/kg	N.D.
----------------------	-------	------

Specimen packed at the moment of acceptance by the laboratory; Mass of specimens: 1.00 ± 0.01 g; Range of the calibration curve: 15 mg/kg - 600 mg/kg; Number of specimens: 3; Detection limit: 16 mg/kg; N.d. - Non detectable; Given the volatility of the molecule in examination, tests performed at different times may yield results which are not comparable.

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR.

1600300-001

REPORT DATE

09/02/2016

(*) 4018021 Determinazione del Pentachlorophenol, Tetrachlorophenol, Trichlorophenol, orto-Phenylphenol

Method: UNI 11057:2003 + UNI EN ISO 17070:2015

Pentachlorophenol (PCP)	mg/Kg	N.D.
2,3,4,5 Tetrachlorophenol (TeCP)	mg/Kg	N.D.
2,3,4,6 Tetrachlorophenol (TeCP)	mg/Kg	N.D.
2,3,5,6 Tetrachlorophenol (TeCP)	mg/Kg	N.D.
2,4,5 Trichlorophenol (TriCP)	mg/Kg	N.D.
2,4,6 Trichlorophenol (TriCP)	mg/Kg	N.D.
2,3,6 Trichlorophenol (TriCP)	mg/Kg	N.D.
2,3,5 Trichlorophenol (TriCP)	mg/Kg	N.D.
3,4,5 Trichlorophenol (TriCP)	mg/Kg	N.D.
2,3,4 Trichlorophenol (TriCP)	mg/Kg	N.D.
orto-Phenylphenol (OPP)	mg/Kg	N.D.
3,4 dichloro phenol (DiCP)	mg/Kg	N.D.
3 chloro phenol (MoCP)	mg/Kg	N.D.
2,4 dichloro phenol (DiCP)	mg/Kg	N.D.
4-chloro-3-methyl phenol (CMP)	mg/Kg	N.D.
2 chloro phenol (MoCP)	mg/Kg	N.D.
2,3 dichloro phenol (DiCP)	mg/Kg	N.D.
3,5 dichloro phenol (DiCP)	mg/Kg	N.D.
2,6 dichloro phenol (DiCP)	mg/Kg	N.D.
4 chloro phenol (MoCP)	mg/Kg	N.D.
2,5 dichloro phenol (DiCP)	mg/Kg	N.D.

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR.

1600300-001

REPORT DATE

09/02/2016

(*) 4019001 Determination of extractable heavy metals A

Method: UNI EN 71-3: 2002 - Determination of extractable heavy metals

Selenium (Se)	mg/Kg	1,0	
Aluminum (Al)	mg/Kg	4,6	
Arsenic (As)	mg/Kg	0,1	
Copper (Cu)	mg/Kg	3,5	
Lead (Pb)	mg/Kg	1,0	
Manganese (Mn)	mg/Kg	1,0	
Mercury (Hg)	mg/Kg	0,5	
Pond (Sn)	mg/Kg	1,0	
Total amount of heavy metals	mg/Kg	12,7	

Apparatus: ICP-MS.

(*) 4919031 Search and dosage metals UV-Vis spectroscopy

Method: PDP 057:2005 REF. CNR-IRSA 3150 MET. C MODIFIED - Search and dosage metals UV-Vis spectroscopy

Chrome (VI)	ppm	N.D.	
-------------	-----	------	--

(*) 4036001 Dimethyl fumarate

Method: PDP 095:2008 - Determination of Dimethyl fumarate

Evidences Found	ppm	N.D.	
-----------------	-----	------	--

References law: European Commission Decision of March 19, 2009 No. 1723; Analytical method used: extraction in water at room temperature, analysis by liquid chromatography; Limit of detection: 0.1 ppm; Maximum of Law: 0.1 ppm; Nr - not detectable, below t

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR.

1600300-001

REPORT DATE

09/02/2016

(*) 4032001 Detection of carcinogenic dyes

Method: PDP 077:2007 - Detection of carcinogenic dyes

ACID RED 26 (16.150) [3761-53-3]	mg/l	N.D.	
BASIC RED 9 (42.500) [569-61-9]	mg/l	N.D.	
DIRECT BLACK 38 (30.235) [1937-37-7]	mg/l	N.D.	
DIRECT BLUE 6 (22.610) [2602-46-2]	mg/l	N.D.	
DIRECT RED 28 (22.120) [573-58-0]	mg/l	N.D.	
BLUE DISPERSED 1 (64.500) [2475-45-8]	mg/l	N.D.	
YELLOW DISPERSED 3 (11.855) [2832-40-8]	mg/l	N.D.	
BASIC VIOLET 14 (42.510) [632-99-5]	mg/l	N.D.	
DISPERSED ORANGE 11 (60.700) [82-28-0]	mg/l	N.D.	
Final result	mg/l	N.D.- PASS	

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
		REPORT NR.	1600300-001
		REPORT DATE	09/02/2016
<p>(*) 4032011 Detection of disperse and allergenic dyes</p> <p>Method: DIN 54231:2004 - Detection of disperse and allergenic dyes</p>			
BLUE DISPERSED 1 (64.500) [2475-45-8]	mg/l	N.D.	
BLUE DISPERSED 3 (61.505) [2475-46-9]	mg/l	N.D.	
BLUE DISPERSED 7 (62.500) [3179-90-6]	mg/l	N.D.	
BLUE DISPERSED 26 (63.305) [3860-63-7]	mg/l	N.D.	
BLUE DISPERSED 35 [12222-75-2]	mg/l	N.D.	
BLUE DISPERSED 102 [12222-97-8]	mg/l	N.D.	
BLUE DISPERSED 106 [122223-01-7]	mg/l	N.D.	
BLUE DISPERSED 124 [61951-51-7]	mg/l	N.D.	
BRUNO DISPERSED 1 [23355-64-8]	mg/l	N.D.	
ORANGE DISPERSED 1 (11.080) [2581-69-3]	mg/l	N.D.	
ORANGE DISPERSED 3 (11.005) [730-40-5]	mg/l	N.D.	
ORANGE DISPERSED 76/37 [122223-33-5]	mg/l	N.D.	
YELLOW DISPERSED 1 (10.345) [199-15-3]	mg/l	N.D.	
YELLOW DISPERSED 3 (11.855) [2832-40-8]	mg/l	N.D.	
YELLOW DISPERSED 9 (10.375) [6373-73-5]	mg/l	N.D.	
YELLOW DISPERSED 39 [12236-29-2]	mg/l	N.D.	
YELLOW DISPERSED 49 [54824-37-2]	mg/l	N.D.	
RED DISPERSED 1 (11.110) [2872-52-8]	mg/l	N.D.	
RED DISPERSED 11 (62.015) [2872-48-2]	mg/l	N.D.	
RED DISPERSED 17 (11.210) [3179-89-3]	mg/l	N.D.	
ORANGE DISPERSED 61 (11.1355)	mg/l	N.D.	
DARK BROWN DISPERSED 4 (11,152:1)	mg/l	N.D.	
Final result	mg/l	N.D.- PASS	

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

		REPORT NR.	1600300-001
		REPORT DATE	09/02/2016
TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹

Unrepeatable tests to exhaustion test material.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

END OF REPORT

Managing Director

Patrizia Rosati



(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.