



VAG AT EX[®]
ITALIA

TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

ARTICLE:	VGT 358 TP LINOLINO
COMPOSITION:	68% VI 32% LI
WEIGHT G/M LIN.:	650 gr/mtl
REPEAT(WARP/WEFT):	NO
METERS PER ROLL:	40/45 MT
WIDHT CM:	140

REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



MADE IN ITALY

www.vagatexitalia.it





- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 4 Color degradation after 6000 giri: 4 END POINT (rubs): > 25.000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 4 At 2000 rubs: 4
Colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5
Colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5 dry: 4 wet: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): Shortening (warp):
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6 warp mm < 6
Fire Resistance	- A: BRITISH 5852 CIGRETTE
Environmental benefits	<ul style="list-style-type: none"> - No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Complies with REACH regulation.
Sustainability	ECO PATH ON REQUEST
Available teflon treatment	ON REQUEST
Type of finish used	STEAM AND DRY AIRO
Tariff code	5516920000
Raw Material & Weaving	Made in Italy



MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1800782-001
REPORT DATE 07/03/2018
ACCEPTANCE DATE 01/03/2018
START TEST DATE 01/03/2018
END TEST DATE 07/03/2018
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION LINOLINO/FR

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD	ACCREDIA
6012001 Assessment of the ignitability of upholstery fabric - Cigarette	BS 5852-1:1979	

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR.	1800782-001
REPORT DATE	07/03/2018
ACCEPTANCE DATE	01/03/2018
START TEST DATE	01/03/2018
END TEST DATE	07/03/2018
SAMPLING BY CUSTOMER	

NOTES ANALYTICAL TESTS

- **6012001 Assessment of the ignitability of upholstery fabric - Cigarette** **BS 5852-1:1979**

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 4 - Part 1 (i.s. 0); Acclimatization: At least 16 hours at 20 ± 5 °C e $50 \% \pm 20 \%$ RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

Filling material: PU non-FR (20-22 Kg/m3) supplied by the laboratory.

Off ignition source.

GENERAL NOTES

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it cant't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1800782-001
REPORT DATE 07/03/2018
 ACCEPTANCE DATE 01/03/2018
 START TEST DATE 01/03/2018
 END TEST DATE 07/03/2018
 SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
6012001 Assessment of the ignitability of upholstery fabric - Cigarette			BS 5852-1:1979
Pretreatment		WATER SOAK 40 °C - 30 MIN	
Kind of sample		COVER FABRIC	
Test 1 - Combustion with flame	Yes/No	NO	
Test 1 - Progressive smouldering	Yes/No	NO	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	Yes/No	NO	
Test 2 - Progressive smouldering	Yes/No	NO	
Test 2 - Result		PASS	

----- **END OF REPORT** -----

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it