



VAG AT EX<sup>®</sup>  
ITALIA

## TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

<b>ARTICLE:</b>	<b>VGT 1215 TP - ARGO</b>
<b>COMPOSITION:</b>	59%VI 29%LI 12%CO
<b>WEIGHT G/M LIN.:</b>	740 gr/mtl
<b>REPEAT(WARP/WEFT):</b>	NO
<b>METERS PER ROLL:</b>	35 MT
<b>WIDHT CM:</b>	140

### REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 4 Color degradation after 6000 giri: 4 END POINT (rubs): > 80.000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 4 At 2000 rubs: 4
Colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5
Colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5      dry: 4 wet: 4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6 warp mm < 6
Fire Resistance	- A: BRITISH STANDARD 5852 CIGRETTE & MATCH
Environmental benefits	- No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Complies with REACH regulation.
Sustainability	ECO PATH ON REQUEST
Available teflon treatment	ON REQUEST
Type of finish used	AIRO WITH SOFTNER + STEAM
Tariff code	5516920000
Raw Material & Weaving	Made in Italy



**MESSRS:**  
**VAGATEX ITALIA SRL**  
**VIA SCARPETTINI 204**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

**REPORT NR.** 1701056-001  
**REPORT DATE** 17/03/2017  
**ACCEPTANCE DATE** 13/03/2017  
**START TEST DATE** 13/03/2017  
**END TEST DATE** 17/03/2017  
**SAMPLING BY CUSTOMER**

## TEST REPORT


SAMPLE DESCRIPTION VGT 1618 TP ARGO FR

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD	ACCREDIA
6012001 Assessment of the ignitability of upholstery fabric - Cigarette	BS 5852-1:1979	
6012002 Assessment of the ignitability of upholstery fabric - Match	BS 5852-1:1979	

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(\*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates **only to the sample tested** and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : [labo@lanartex.it](mailto:labo@lanartex.it) - web : [www.lanartex.it](http://www.lanartex.it)

## TEST REPORT

**MESSRS:**  
**VAGATEX ITALIA SRL**  
**VIA SCARPETTINI 204**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

<b>REPORT NR.</b>	<b>1701056-001</b>
<b>REPORT DATE</b>	<b>17/03/2017</b>
ACCEPTANCE DATE	13/03/2017
START TEST DATE	13/03/2017
END TEST DATE	17/03/2017
SAMPLING BY CUSTOMER	

## NOTES ANALYTICAL TESTS

• **6012001 Assessment of the ignitability of upholstery fabric - Cigarette** **BS 5852-1:1979**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 4 - Part 1 (i.s. 0); Acclimatization: At least 16 hours at  $20 \pm 5$  °C e  $50 \% \pm 20 \%$  RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

Filling material: PU non-FR (20-22 Kg/m<sup>3</sup>) SS20 supplied by the laboratory.

• **6012002 Assessment of the ignitability of upholstery fabric - Match** **BS 5852-1:1979**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at  $20 \pm 5$  °C e  $50 \% \pm 20 \%$  RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

Filling material: PU non-FR (20-22 Kg/m<sup>3</sup>) SS20 supplied by the laboratory.

## GENERAL NOTES

(\*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it cant't also be used to imply the products certification.

The results contained in this report relates **only to the sample tested** and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : [labo@lanartex.it](mailto:labo@lanartex.it) - web : [www.lanartex.it](http://www.lanartex.it)

## TEST REPORT

**MESSRS:**  
**VAGATEX ITALIA SRL**  
**VIA SCARPETTINI 204**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

**REPORT NR.** **1701056-001**  
**REPORT DATE** **17/03/2017**  
**ACCEPTANCE DATE** 13/03/2017  
**START TEST DATE** 13/03/2017  
**END TEST DATE** 17/03/2017  
**SAMPLING BY CUSTOMER**

Tests	M.U.	Results	Method
<b>6012001 Assessment of the ignitability of upholstery fabric - Cigarette</b>			BS 5852-1:1979
Pretreatment		<b>WATER SOAK 40 °C - 30 MIN</b>	
Kind of sample		<b>COVER FABRIC</b>	
Test 1 - Combustion with flame		<b>NO</b>	
Test 1 - Progressive smouldering		<b>NO</b>	
Test 1 - Result		<b>PASS</b>	
Test 2 - Combustion with flame		<b>NO</b>	
Test 2 - Progressive smouldering		<b>NO</b>	
Test 2 - Result		<b>PASS</b>	
<b>6012002 Assessment of the ignitability of upholstery fabric - Match</b>			BS 5852-1:1979
Pretreatment		<b>WATER SOAK 40 °C - 30 MIN</b>	
Kind of sample		<b>COVER FABRIC</b>	
Test 1 - Combustion with flame		<b>1"</b>	
Test 1 - Progressive smouldering		<b>15"</b>	
Test 1 - Result		<b>PASS</b>	
Test 2 - Combustion with flame		<b>2"</b>	
Test 2 - Progressive smouldering		<b>18"</b>	
Test 2 - Result		<b>PASS</b>	

----- **END OF REPORT** -----

(\*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates **only to the sample tested** and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)  
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : [labo@lanartex.it](mailto:labo@lanartex.it) - web : [www.lanartex.it](http://www.lanartex.it)