



VAG AT EX<sup>®</sup>  
ITALIA

## TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

<b>ARTICLE:</b>	VGT 1615 TP - 2D
<b>COMPOSITION:</b>	46%WO 30%PA 18%PL 6%EA
<b>WEIGHT G/M LIN.:</b>	875 gr/mtl
<b>REPEAT(WARP/WEFT):</b>	NO
<b>METERS PER ROLL:</b>	25/30 MT
<b>WIDHT CM:</b>	140

### REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



MADE IN ITALY

[www.vagatexitalia.it](http://www.vagatexitalia.it)





- Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A	Color degradation after 3000 giri: 4/5 Color degradation after 6000 giri: 4/5 END POINT (rubs): > 50.000
Pilling resistance by the modified martindale method UNI EN ISO 12945-2	Degradation average photographic scale 1/5 : 4 At 2000 rubs: 4/5
Colour fastness to light UNI EN ISO 105-B02	Blue scale 1/8 result: 4/5
Colour fastness to rubbing UNI EN ISO 105-X12	Grey scale 1/5      dry: 4 wet: 3/4
Dimensional change after washing UNI EN ISO 6330	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Dimensional change after dry cleaning UNI EN ISO 3175	Narrowing (weft): <= +/-3% Shortening (warp): <= +/-3%
Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465)	Weft mm < 6  warp mm < 6
Fire Resistance	- A: BRITISH STANDARD 5852 CIGRETTE & MATCH - B: CRIB V - C: CLASS 1 ITALY
Environmental benefits	- No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Complies with REACH regulation.
Sustainability	ECO PATH ON REQUEST
Available teflon treatment	ON REQUEST
Type of finish used	EXCLUSIVE FINISH
Tariff code	6004100091
Raw Material & Weaving	Made in Italy



**MESSRS.:**  
**VAGATEX ITALIA SRL**  
**VIA SCARPETTINI 204**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

**REPORT NR.** 1403348-002  
**REPORT DATE** 22/10/2014  
ACCEPTANCE DATE 16/10/2014  
START TEST DATE 16/10/2014  
END TEST DATE 22/10/2014  
SAMPLING BY CUSTOMER

## TEST REPORT

SAMPLE DESCRIPTION: VGT 1615 TP - 2D

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY <sup>1</sup>
<b>6012001 Assessment of the ignitability of upholstery fabric - Cigarette</b>			
<b>Method:</b> BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Cigarette			
Test 1 - Combustion with flame	min	0	
Test 1 - Progressive smouldering	sec	0	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	sec	0	
Test 2 - Progressive smouldering	sec	0	
Test 2 - Result		PASS	

Filling material: PU non-FR (20-22 Kg/m<sup>3</sup>) SS20 supplied by the laboratory.  
Pretreatment: None

Off ignition source.

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 4 - Part 1 (i.s. 0); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.



# LABORATORIO PROVE, ANALISI RICERCHE TESSILI

LANARTEX di Rosati Patrizia & C. Sas  
Via I° Maggio, 27  
59013 Montemurlo (PO)  
Tel. 0574-071701 Fax: 0574-899903  
e-mail: labo@lanartex.it  
Partita IVA: 02055730978



LAB n° 0572

		<b>REPORT NR.</b>	<b>1403348-002</b>
		<b>REPORT DATE</b>	<b>22/10/2014</b>
<b>TEST</b>	<b>M.U.</b>	<b>RESULTS</b>	<b>EXPANDED UNCERTAINTY <sup>1</sup></b>

## 6012002 Assessment of the ignitability of upholstery fabric - Match

**Method:** BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Match

Test 1 - Combustion with flame	min	0
Test 1 - Progressive smouldering	sec	4
Test 1 - Result		PASS
Test 2 - Combustion with flame	sec	0
Test 2 - Progressive smouldering	sec	5
Test 2 - Result		PASS

Filling material: PU non-FR (20-22 Kg/m<sup>3</sup>) SS20 supplied by the laboratory.  
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989, 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

-----  
**END OF REPORT**  
-----

**Managing Director**

Patrizia Rosati  
-----

**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

## RAPPORTO PROVA

CLIENTE: VAGATEX

ARTICOLO: VGT 1615 TP - 2D

DATA: 01/08/20124

### DESCRIZIONE ARTICOLO:

Tessuto nero accoppiato a rete rossa, impregnazione Firex I63: 300 g/l.

### **SIMULAZIONE NORMA UNI8456**

Reazione al fuoco di materiali combustibili suscettibili di essere investiti da una piccola fiamma su entrambe le facce.

### **AL MANUFATTO VIENE ATTRIBUITA LA CATEGORIA 1 ITALIA**

N.B. I test effettuati sono puramente indicativi e sono realizzati mediante una simulazione di laboratorio del metodo in questione. Per una certificazione dell'articolo, si raccomanda in ogni caso di rivolgersi agli opportuni enti.

**Responsabile Operativo**

FARAGI Sebastiano

**MESSRS:**  
**VAGATEX ITALIA SRL**  
**Via Labriola, 247**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

**REPORT NR. 1802153-001**  
**REPORT DATE 06/06/2018**  
ACCEPTANCE DATE 06/06/2018  
START TEST DATE 06/06/2018  
END TEST DATE 06/06/2018  
SAMPLING BY CUSTOMER

## TEST REPORT


SAMPLE DESCRIPTION VGT 1615 TP - 2D

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST	METHOD	ACCREDIA
6012053 Assessment of the ignitability of upholstery fabric - Crib 5	BS 5852:2006	

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(\*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : [labo@lanartex.it](mailto:labo@lanartex.it) - web : [www.lanartex.it](http://www.lanartex.it)

## TEST REPORT

**MESSRS:**  
**VAGATEX ITALIA SRL**  
**Via Labriola, 247**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

<b>REPORT NR.</b>	<b>1802153-001</b>
<b>REPORT DATE</b>	<b>06/06/2018</b>
ACCEPTANCE DATE	06/06/2018
START TEST DATE	06/06/2018
END TEST DATE	06/06/2018
SAMPLING BY CUSTOMER	

## NOTES ANALYTICAL TESTS

• **6012053 Assessment of the ignitability of upholstery fabric - Crib 5 BS 5852:2006**

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use; Acclimatization: At least 24 hours at  $23 \pm 2$  °C e  $50 \% \pm 5 \%$  RH; Ignition source (i.s.): Ignition source 5 - Crib 5;

Maps of results:

- N.I./5 - Not ignited (Pass the test);

- I/5 - Burn with crib 5 (Fail the test).

Filling material: PU-FR (30-33 Kg/m3) supplied by the laboratory.

## GENERAL NOTES

Unrepeatable tests to exhaustion test material.

(\*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : [labo@lanartex.it](mailto:labo@lanartex.it) - web : [www.lanartex.it](http://www.lanartex.it)

## TEST REPORT

**MESSRS:**  
**VAGATEX ITALIA SRL**  
**Via Labriola, 247**  
**59013 MONTEMURLO (PO)**  
**ITALIA**

**REPORT NR. 1802153-001**  
**REPORT DATE 06/06/2018**  
 ACCEPTANCE DATE 06/06/2018  
 START TEST DATE 06/06/2018  
 END TEST DATE 06/06/2018  
 SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
<b>6012053 Assessment of the ignitability of upholstery fabric - Crib 5</b>			BS 5852:2006
Kind of sample		<b>COVER FABRIC</b>	
Pretreatment		<b>NONE AS AGREED WITH THE CUSTOMER</b>	
Test 1 - Combustion with flame	s	<b>296</b>	
Test 1 - Progressive smouldering	s	<b>322</b>	
Test 1 - Result		<b>N.I./5</b>	
Test 2 - Combustion with flame	s	<b>280</b>	
Test 2 - Progressive smouldering	s	<b>312</b>	
Test 2 - Result		<b>N.I./5</b>	

----- **END OF REPORT** -----

(\*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)  
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : [labo@lanartex.it](mailto:labo@lanartex.it) - web : [www.lanartex.it](http://www.lanartex.it)



**SPETTABILE:**

**VAGATEX ITALIA SRL  
VIA SCARPETTINI 204  
59013 MONTEMURLO (PO)  
ITALIA**

**RAPPORTO DI PROVA NR 1402621-001**  
**DATA DI EMISSIONE 16/07/2014**  
DATA RICEVIMENTO CAMPIONI 14/07/2014  
DATA ACCETTAZIONE E INIZIO PROVE 14/07/2014  
DATA FINE PROVE 16/07/2014  
CAMPIONAMENTO EFFETTUATO DAL COMMITTENTE

## RAPPORTO DI PROVA

DENOMINAZIONE DEL CAMPIONE: VGT 1615 TP - 2D

PROVA	U.M.	RISULTATO	INCERTEZZA
<b>2032052 Determinazione della tendenza alla formazione di peluria superficiale e palline (pilling) - Metodo Martindale - Arredamento</b>			
<b>Metodo:</b>	UNI EN ISO 12945-2:2002 - Determinazione della tendenza alla formazione di peluria superficiale e palline (pilling) - Metodo Martindale		
Caratteristica valutata		PILLING E FUZZING	
Numero di provette		3	
Pretrattamento		NESSUNO	
Mezzo abrasivo		LANA STANDARD	
Valutazione a 500 sfregamenti		4-5	
Valutazione a 1.000 sfregamenti		4-5	
Valutazione a 2.000 sfregamenti		4	
Valutazione a 5.000 sfregamenti		4	

Tipologia campione: tessuto a maglia - Uso arredamento  
Carico applicato: 415±2g

I campioni da testare sono stati condizionati in ambiente a 20±2°C e 65±4%UR conformemente alla norma UNI EN ISO 139; Valutazione eseguita per confronto con standard fotografici e/o valutazione visiva secondo lo schema seguente: 1 - Densa formazione di peluria e/o densa formazione di palline. Pilling di varie dimensioni che copre densamente l'intera superficie del campione; 2 - Discreta formazione di peluria superficiale e/o discreta formazione di palline. Pilling di varie dimensioni che copre una larga parte della superficie del campione; 3 - Moderata formazione di peluria e/o moderata formazione di palline. Pilling di varie dimensioni che copre parzialmente la superficie del campione; 4 - Leggera formazione di peluria e/o parzialmente aggregata in palline; 5 - Nessun Cambiamento.

**(\*) = Le prove contrassegnate con asterisco non sono accreditate Accredia.**

U = Incertezza di misura calcolata dal laboratorio al valore limite di 0,5. L'incertezza estesa è ottenuta moltiplicando l'incertezza tipo composta per un fattore di copertura K=2, stimata al 95% di probabilità.



# LABORATORIO PROVE, ANALISI RICERCHE TESSILI

LANARTEX di Rosati Patrizia & C. Sas  
Via I° Maggio, 27  
59013 Montemurlo (PO)  
Tel. 0574-071701 Fax: 0574-899903  
e-mail: labo@lanartex.it  
Partita IVA: 02055730978



LAB n° 0572

## RAPPORTO DI PROVA NR 1402621-001

DATA DI EMISSIONE 16/07/2014

PROVA	U.M.	RISULTATO	INCERTEZZA
-------	------	-----------	------------

I Risultati contenuti nel presente Rapporto si riferiscono esclusivamente al campione esaminato e non alla partita/lotto che vogliono rappresentare. Il presente Rapporto di Prova non può essere riprodotto parzialmente senza autorizzazione scritta da parte di LANARTEX. Le prove contrassegnate con (\*) non sono accreditate ACCREDIA. Limitazioni all'uso del marchio ACCREDIA: LANARTEX è un laboratorio accreditato ACCREDIA e pertanto adempie agli obblighi derivanti dalla convenzione con esso stipulata. Il marchio ACCREDIA non può essere apposto sui materiali sottoposti a prova, non può essere utilizzato per sottintendere la certificazione di prodotto.

Fine del presente rapporto di prova

**Direzione Generale**

Patrizia Rosati

**(\*) = Le prove contrassegnate con asterisco non sono accreditate Accredia.**

U = Incertezza di misura calcolata dal laboratorio al valore limite di 0,5. L'incertezza estesa è ottenuta moltiplicando l'incertezza tipo composta per un fattore di copertura K=2, stimata al 95% di probabilità.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it