



VAG A T E X [®]
I T A L I A

TECHNICAL SHEET

(according to the standard UNI EN ISO 14465)

| | |
|---------------------------|------------------------------|
| ARTICLE: | VGT 2262 TF - ECLISSI |
| COMPOSITION: | 43% PL 23% CO 17% VI 17% LI |
| WEIGHT G/M LIN.: | 644 gr/mtl |
| REPEAT(WARP/WEFT): | NO |
| METERS PER ROLL: | 40 MT |
| WIDHT CM: | 140 |

REGULAR CARE AND LEGAL GUARANTEE:

Regular cleaning is important to keep the upholstery fabric looking its best and to extend its life. The guarantee is subject to the correct use of the fabric and its maintenance.

It is usually recommended that upholstered furniture with normal commercial use should be cleaned 2-3 times a year.

Upholsteries in private households usually need less frequent cleaning. In order to ensure satisfying cleaning results, we recommend to contact a professional cleaning institute.

Please follow the maintenance instructions of the technical data sheet.



| | |
|---|--|
| - Abrasion Resistance - Martindale UNI EN ISO 12947-2 + EN 14465, appendice A | Color degradation after 3000 giri: 4/5 Color degradation after 6000 giri: 4/5 END POINT (rubs): > 30.000 |
| Pilling resistance by the modified martindale method UNI EN ISO 12945-2 | Degradation average photographic scale 1/5 : 4 At 2000 rubs: 4/5 |
| Colour fastness to light UNI EN ISO 105-B02 | Blue scale 1/8 result: 4/5 |
| Colour fastness to rubbing UNI EN ISO 105-X12 | Grey scale 1/5 dry: 4 wet: 3/4 |
| Dimensional change after washing UNI EN ISO 6330 | Narrowing (weft): <= +-3% Shortening (warp): <= +-3% |
| Dimensional change after dry cleaning UNI EN ISO 3175 | Narrowing (weft): <= +-3% Shortening (warp): <= +-3% |
| Resistance to yarn Slippage at stitched seams UNI EN ISO 13937-3 (din 14465) | Weft mm < 6 warp mm < 6 |
| Fire Resistance | - A: BS 5852 MATCH & CIGARETTE - B: other test available on request |
| Environmental benefits | - No use of AZO dyes, which may split off carcinogenic acrylic amines. - No use of dyes containing heavy metals/complies with ETAD norm. - No use of brominated flame retardants. - Complies with REACH regulation. |
| Sustainability | ECO-PATH (available on request) |
| Available teflon treatment | (on request) |
| Type of finish used | STEAM + ENAIRGY |
| Tariff code | 5514309000 |
| Raw Material & Weaving | Made in Italy |

| | | | | | |
|---|--------------------|---|---|--|---|
|  | on the back fabric |  |  |  |  |
|---|--------------------|---|---|--|---|

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1900636-002
REPORT DATE 25/02/2019
ACCEPTANCE DATE 20/02/2019
START TEST DATE 20/02/2019
END TEST DATE 25/02/2019
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION FABRIC ART. VGT 2262 TF

THE REPORT IS MADE BY THE FOLLOWING TESTS:

| TEST | METHOD | ACCREDIA |
|---|----------------|----------|
| 6012001 Assessment of the ignitability of upholstery fabric - Cigarette | BS 5852-1:1979 | |
| 6012002 Assessment of the ignitability of upholstery fabric - Match | BS 5852-1:1979 | |

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

| | |
|----------------------|--------------------|
| REPORT NR. | 1900636-002 |
| REPORT DATE | 25/02/2019 |
| ACCEPTANCE DATE | 20/02/2019 |
| START TEST DATE | 20/02/2019 |
| END TEST DATE | 25/02/2019 |
| SAMPLING BY CUSTOMER | |

NOTES ANALYTICAL TESTS

• **6012001 Assessment of the ignitability of upholstery fabric - Cigarette** **BS 5852-1:1979**

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 4 - Part 1 (i.s. 0);

All outer covers that have been chemically treated to reduce their ignitability shall be subjected to the water soaking and drying procedure prior to being conditioned. This requirement applies to all methods of treatment, including back coating, which are applied to material covers that are finished in all other respects. It does not apply when the cover material is manufactured from materials that are formulated to be, or are inherently, flame retardant. Where it is not known whether the material has been so treated or not, the water soaking and drying procedure shall be carried out.

Acclimatization: At least 16 hours at 20 ± 5 °C e 50 ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.

• **6012002 Assessment of the ignitability of upholstery fabric - Match** **BS 5852-1:1979**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 5 - Part 1 (i.s. 1);

All outer covers that have been chemically treated to reduce their ignitability shall be subjected to the water soaking and drying procedure prior to being conditioned. This requirement applies to all methods of treatment, including back coating, which are applied to material covers that are finished in all other respects. It does not apply when the cover material is manufactured from materials that are formulated to be, or are inherently, flame retardant. Where it is not known whether the material has been so treated or not, the water soaking and drying procedure shall be carried out.

Acclimatization: At least 16 hours at 20 ± 5 °C e 50 ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.

GENERAL NOTES

Unrepeatable tests to exhaustion test material.

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it cant't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. **1900636-002**
REPORT DATE **25/02/2019**
ACCEPTANCE DATE 20/02/2019
START TEST DATE 20/02/2019
END TEST DATE 25/02/2019
SAMPLING BY CUSTOMER

| Tests | M.U. | Results | Method |
|--|--------|---|----------------|
| 6012001 Assessment of the ignitability of upholstery fabric - Cigarette | | | BS 5852-1:1979 |
| Data declared by the customer | | Sample chemically treated to reduce the ignitability | |
| Pretreatment | | Water soak 40 °C - 30 min | |
| Kind of sample | | Cover fabric | |
| Test 1 - Combustion with flame | Yes/No | NO | |
| Test 1 - Progressive smouldering | Yes/No | NO | |
| Test 1 - Result | | PASS | |
| Test 2 - Combustion with flame | Yes/No | NO | |
| Test 2 - Progressive smouldering | Yes/No | NO | |
| Test 2 - Result | | PASS | |
| 6012002 Assessment of the ignitability of upholstery fabric - Match | | | BS 5852-1:1979 |
| Data declared by the customer | | Sample chemically treated to reduce the ignitability | |
| Pretreatment | | Water soak 40 °C - 30 min | |
| Kind of sample | | Cover fabric | |
| Test 1 - Combustion with flame | s | >120 | |
| Test 1 - Progressive smouldering | s | - | |
| Test 1 - Result | | FAIL | |

----- **END OF REPORT** -----

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1900911-001
REPORT DATE 12/03/2019
ACCEPTANCE DATE 08/03/2019
START TEST DATE 08/03/2019
END TEST DATE 12/03/2019
SAMPLING BY CUSTOMER

TEST REPORT


SAMPLE DESCRIPTION FABRIC ART. VGT 2262 TF

THE REPORT IS MADE BY THE FOLLOWING TESTS:

| TEST | METHOD | ACCREDIA |
|---|----------------|----------|
| 6012002 Assessment of the ignitability of upholstery fabric - Match | BS 5852-1:1979 | |

Technical Manager

Dott.ssa Valentina Guidotti



Managing Director

Patrizia Rosati



(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

| | |
|----------------------|--------------------|
| REPORT NR. | 1900911-001 |
| REPORT DATE | 12/03/2019 |
| ACCEPTANCE DATE | 08/03/2019 |
| START TEST DATE | 08/03/2019 |
| END TEST DATE | 12/03/2019 |
| SAMPLING BY CUSTOMER | |

NOTES ANALYTICAL TESTS

• **6012002 Assessment of the ignitability of upholstery fabric - Match BS 5852-1:1979**

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 5 - Part 1 (i.s. 1);

All outer covers that have been chemically treated to reduce their ignitability shall be subjected to the water soaking and drying procedure prior to being conditioned. This requirement applies to all methods of treatment, including back coating, which are applied to material covers that are finished in all other respects. It does not apply when the cover material is manufactured from materials that are formulated to be, or are inherently, flame retardant. Where it is not known whether the material has been so treated or not, the water soaking and drying procedure shall be carried out.

Acclimatization: At least 16 hours at 20 ± 5 °C e $50 \% \pm 20$ % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

Filling material: PU non-FR (20-22 Kg/m³) SS20 supplied by the laboratory.

GENERAL NOTES

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it cant't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

TEST REPORT

MESSRS:
VAGATEX ITALIA SRL
Via Labriola, 247
59013 MONTEMURLO (PO)
ITALIA

REPORT NR. 1900911-001
REPORT DATE 12/03/2019
ACCEPTANCE DATE 08/03/2019
START TEST DATE 08/03/2019
END TEST DATE 12/03/2019
SAMPLING BY CUSTOMER

| Tests | M.U. | Results | Method |
|--|------|---|----------------|
| 6012002 Assessment of the ignitability of upholstery fabric - Match | | | BS 5852-1:1979 |
| Data declared by the customer | | Sample chemically treated to reduce the ignitability | |
| Pretreatment | | Water soak 40 °C - 30 min | |
| Kind of sample | | Cover fabric | |
| Test 1 - Combustion with flame | s | 2 | |
| Test 1 - Progressive smouldering | s | 16 | |
| Test 1 - Result | | PASS | |
| Test 2 - Combustion with flame | s | 0 | |
| Test 2 - Progressive smouldering | s | 13 | |
| Test 2 - Result | | PASS | |

----- **END OF REPORT** -----

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
 Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it